



ALTA 85 POLYUREA JOINT FILLER

100% Solids, Self-Leveling Polyurea Caulking Compound

Product Series #2500

PRODUCTION DESCRIPTION

Alta 85 is a two-component aromatic, 1:1 ratio, rapid setting, self-leveling, 100% solids polyurea joint filling compound for interior and exterior horizontal application.

FEATURES

- » Flexible
- » Shave Time 30-90 Minutes
- » Odorless
- » Meets UDSA Criteria
- » Non-Toxic
- » Remains Flexible, Even In Cold Temperatures
- » Meets California VOC and AQMD Requirement

TYPICAL USES

Alta 85 is used on interior and exterior horizontal concrete surfaces, to repair random cracks, control joints, and other areas where down time is limited.

- » Truck Aprons
- » Bridge Headers
- » Cold Storage
- » Wastewater Plants
- » Parking Garage Decks
- » Warehouses
- » Airports
- » Spalls
- » Food Processing Plants
- » Saw/Utility Cuts

COLOR

- » Natural
- » Standard Gray
- » Graphite Gray

PACKAGING

- 10-gallon kit One 5 gallon (18.9 liters) pail of Side-A and One 5 gallon (18.9 liters) pail of Side-B
- 100-gallon kit One 55 gallon drum (net 50 gallons, 189 liters) of Side-A and One 55 gallon drum (net 50 gallons, 189 liters) of Side-B

*Also available in a 22oz Dual Packs.

COVERAGE

Coverage's and yields shown do not include allowances for loss or waste and variations in job conditions. Each user must establish their own factors for loss from experience.

		Width of Joint						
		1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
Depth of Joint	1/4"	308	205	154	123	102	88	77
	3/8"	205	136	102	82	68	58	51
	1/2"	154	102	77	61	51	44	38
	5/8"	123	82	61	49	41	35	30
	3/4"	102	68	51	41	34	29	25
	7/8"	88	58	44	36	29	25	22
	1"	77	51	38	30	25	22	19

SURFACE PREPARATION

Allow concrete to cure 28 days before installation. Saw cut the joint to ACI Recommendations. All joints must be clean and dry prior to installing Alta Paints 85 Polyurea Joint Filler.

If joint is damp, dry with heat torch. If primer is required, consult with your Alta Paints and Coating representative for the most appropriate primer product.

Remove all dust from the concrete pores prior to installing Alta Paints 85 Polyurea Joint Filler. If backer rod is used in control joints, the recommended depth is not greater than 25% of the total depth of the slab.

Shave off any over-pour flush to grade. Open to traffic once Alta 85 has set. Surface can be utilized to light traffic typically within 90 minutes of application.

Construction joints are to be filled to full depth using no backer rod or silica sand. To repair T-joints, the joint should be cut a minimum of 25% of the total depth of the slab. The side of the T-joint must be cut 12" (20.4cm) from the joint and a minimum of 2" (5.08 cm) deep.

MIXING

Alta Paints 85 Polyurea Joint Filler may not be diluted under any circumstance. Side-A material requires no mixing. Pre-mix Side-B material before application using a mechanical mixer at a low speed. Mix until a homogeneous mixture and color is achieved.

Do not mix in an up and down motion. Use only a proportioning dispensing system which transfers, meters and mixes the Side-A with Side-B components at the desired rate and at the required proportion of 1:1 by volume.

APPLICATION

For best results, machine dispense using a 1:1 ratio pump, with or without heater as required. Use a disposable static mixing tube with restrictor before dispensing. Material left in static mixing tube will thicken in approximately 30-60 seconds and mixing tube needs to be discarded at that point. This material can be applied at environmental temperatures from 20°F (6.6°C) to as high as 135°F (57°C). The product needs to be conditioned at 75-80°F (25-27°C) prior to use.

*22oz Dual Packs can be applied using a dual cartridge.

FINISHING

Shave off any over-pour flush to grade. Open to traffic once Alta Paints 85 Polyurea Joint Filler has set. Surface can be utilized to light traffic typically within 90 minutes of application.

CLEAN UP

Cured product may be disposed of without restriction. Mix excess Side-A with Side-B material and allow to cure. Check local, state and federal laws before disposing of material.

LIMITATIONS

Discoloration will occur if exposed to UV, however no change will occur in the physical properties.

STORAGE

Alta Paints 85 Polyurea Joint Filler has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

TECHNICAL DATA (BASED ON DRAW DOWN FILM)

Mix Ratio by Volume	1A : 1B
Specific Gravity, Side A Side B	1.12 ± 0.1 1.07 ± 0.1
Viscosity at 75°F (24°C), Side A Side B	1100 ± 200 cps 1200 ± 200 cps
Gel Time at 75°F (24°C), ASTM D-2471	35 ± 5 seconds
Hardness, ASTM D-2240	80 ± 5 Shore A
Tensile Strength, ASTM D-412	1500 ± 200 psi 10.3 ± 1.4 MPa
Elongation, ASTM D-412	300 ± 50%
Tear Strength, ASTM D-624	275 ± 50 pli 48.2 ± 8.8 kNm
Total Solids by Weight, ASTM D-2669	95 ± 2%
Total Solids by Volume, ASTM D-2697	95 ± 2%

Warning: This product contains Isocyanates and Solvent.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer